



## SPECIFICATION

## Advanced LIGO Input Test Mass Coatings

AUTHOR:	CHECKED:	DATE	APPROVALS		
			DCN NO.	REV	DATE
R. Dannenberg	G. Billingsley	3/20/09			

Name	Input Test Mass (ITM)
<b>Applicable Documents</b>	
<b>Blank Specification</b>	D080657-v1
<b>Blank Drawing</b>	D080039
<b>Polish Specification</b>	E080511-v2
<b>Polish Drawing</b>	D080657 - A
<b>Coating Specification</b>	E0900041-v3
<b>Fabricate From</b>	D080657 - A
<b>Surface Quality (Scratch Total Area)</b>	
<b>Max Scratches Surface 1 inside 120mm diameter ( units of <math>\mu\text{m}^2</math>)</b>	20000
<b>Max Scratches Surface 1 outside 120mm to 160 mm diameter ( units of <math>\mu\text{m}^2</math>)</b>	500000
<b>Max Scratches Surface 2 inside 120mm diameter ( units of <math>\mu\text{m}^2</math>)</b>	240000
<b>Surface Quality (Total Defect Number)</b>	
<b>Max Point Defects Surface 1 inside 120mm diameter</b>	10



**Advanced LIGO Input Test Mass Coatings**

<b>Max Point Defect Density Surface 1 inside 120 mm diameter</b>	1 per 4 mm <sup>2</sup>
<b>Max Point Defects Surface 1 outside 120 mm to 160 mm diameter</b>	100
<b>Max Point Defects Surface 2 inside 120 mm diameter</b>	100
<b>General to All Surfaces</b>	
<b>Coating Thickness Uniformity</b>	Fractional Change <0.001 over 160 mm diameter. If the physical thickness variation of the coating cannot be measured with a profilometer or inferred interferometrically, it may be inferred from the wavelength shift of the coating as a function of position.
<b>Coating Relative Wavelength Uniformity</b>	Fractional Change <0.001 over 160 mm diameter.
<b>Coating Area</b>	To Bevel
<b>Witness Sample Durability Testing</b>	Once Witness Piece Per Run:  Coating to resist adhesion test per MIL-C-48497A 4.5.3.1 Adhesion (snap tape).  MIL-C-4.5.3.2 Humidity (120F 95% RH for 24 hours), combined with before/after spectrophotometer scan from 400 - 2500 nm, marking the specimen ensure the same area is scanned. There should be no measureable spectral shift.  MIL-C-4.5.3.3 Moderate Abrasion (cheesecloth rub).
<b>Surface 1</b>	<b>NOTE: ARROWS ON OPTIC SIDES POINT TO SURFACE 1</b>
<b>Coating Type</b>	High Reflection



**Advanced LIGO Input Test Mass Coatings**

<p><b>Angle of Incidence</b></p>	<p>Normal</p>
<p><b>Transmission at 1064 nm</b></p>	<p>0.013 - 0.015 requirement [See Transmittance Matching Explanation]</p>
<p><b>Transmission Matching Between Parts at 1064 nm</b></p>	<p><b>REQUIREMENT:</b></p> <p>The central transmission range is 0.013 - 0.015, within that range there are 3 mirror-triplets satisfying <math>2  (T1-T2)/(T1+T2)  &lt; 0.01</math>.</p> <p><b>EASIER GOAL:</b></p> <p>The central transmission range is 0.013 - 0.015, and somewhere within that range all 10 mirrors satisfy <math>2  (T1-T2)/(T1+T2)  &lt; 0.01</math>.</p> <p><b>HARDER GOAL:</b></p> <p>All 10 ITM Surface 1 coatings fall within the range <math>0.014 \pm 7E-5</math>, where the <math>2  (T1-T2)/(T1+T2)  &lt; 0.01</math> matching specification is automatically met.</p> <p>T1 = maximum transmittance &amp; T2 = minimum transmittance for triplets of parts in the requirement, or all parts in the goals.</p>
<p><b>Transmission at 532 nm</b></p>	<p>&lt;0.01, goal 0.001</p>
<p><b>Thermal Stability at 532 nm</b></p>	<p><math>2  (T1-T2)/(T1+T2)  &lt; 0.1</math> for T1 = 25 °C to T2=40 °C</p>
<p><b>Thermal Stability at 1064 nm</b></p>	<p><math>2  (T1-T2)/(T1+T2)  &lt; 0.01</math> for T1 = 25 °C to T2 = 40 °C</p>

## Advanced LIGO Input Test Mass Coatings

<b>Coating Materials</b>	The coating is comprised of silicon-dioxide layers alternating with layers tantalum pentoxide doped with 25% (by cation) titanium dioxide.
<b>Surface Electric Field 1064 nm</b>	$E < 0.01$ V/m. Vendor must demonstrate through calculation using $E$ [V/m] = $27.46 (T / \text{Re}(Y))^{0.5}$ , with T being the transmittance and Y the surface admittance in free space units.
<b>Thermal Noise</b>	<p><math>&lt; 3.6 \cdot 10^{-21}</math> m/<math>\sqrt{\text{Hz}}</math> at 100 Hz – This is to be calculated from the material layer thicknesses, other parameters provided by LIGO, and by a formula provided by LIGO.</p> <p>The requirement is that using the provided formula, the predicted thermal noise should be below this level, the goal is to get as low a thermal noise as possible.</p> <p>This is to be done on a best-effort basis with no warranty or guarantee of suitability of use for any application</p>
<b>Surface 2</b>	
<b>Coating Type</b>	Antireflection
<b>Angle of Incidence</b>	Normal
<b>Reflection at 1064 nm</b>	$< 50$ ppm requirement, goal $< 20$ ppm
<b>Reflection at 532 nm</b>	N/A
<b>Surface Electric Field</b>	N/A
<b>Scatter</b>	N/A
<b>Absorption</b>	$< 1$ ppm requirement.
<b>Thermal Stability at 532 nm</b>	N/A



**Advanced LIGO Input Test Mass Coatings**

<b>Thermal Stability at 1064 nm</b>	$2  (T1-T2)/(T1+T2)  < 0.01$ for T1 = 25 °C to T2 = 40 °C
<b>Coating Materials</b>	N/A
<b>Other</b>	
<b>Additional Deliverables</b>	
<b>1. Witness Samples</b>	Ten 1-inch witness samples, provided by LIGO, from each coating run
<b>2. Measured and Design Layer Thicknesses</b>	For all layers in the design, measured thickness data from the deposition for each run), designed thicknesses, and measured indices of refraction at both 1064 nm and 532 nm for both coating materials (based on individual layers).
<b>3. Surface 1 Spectrophotometer Scans</b>	On a representative witness piece for each run, spectrophotometer graphs of reflectance and transmission of Surface 1 (HR coating) from 350-2500 nm before it is coated, between Surface 1 and Surface 2 coating, and after coating is completed. LIGO's preference is to have all spectrophotometer data be provided in Excel spreadsheet format.
<b>4. Surface 2 Spectrophotometer Scans</b>	On a representative witness piece for each run, spectrophotometer graph of reflectance of Surface 2 (AR coating) from 350-2500 nm before it is coated, between Surface 1 and Surface 2 coating, and after coating is completed. LIGO's preference is to have all spectrophotometer data be provided in Excel spreadsheet format.
<b>5. Scatter Maps.</b>	Maps of scatter, absorption, and transmission over central 160 mm diameter with optic orientation specified. Scatter should be measured accurately to ± 1 ppm, absorption to ± 0.1 ppm, and transmission to ± 0.001.

## Advanced LIGO Input Test Mass Coatings

<p><b>6. Scratches &amp; Point Defects Methods 1&amp;2 (Hand Sketch).</b></p>	<p><b>METHOD 1.</b></p> <p>The surface is examined visually by two observers independently. The examination is done against a dark background using a fiber optic illumination system of at least 200 W total power. A 100% inspection of the surface is carried out. Pits and scratches down to 2 micrometers in width can be detected using this method of inspection. Any scratches or sleeks that are detected will be measured using a calibrated eyepiece.</p> <p><b>METHOD 2.</b></p> <p>Further inspection will be done with a minimum 6X eyeglass using the same illumination conditions, again with two observers. Sleeks down to 0.5 micrometers wide can be detected using this method. The surface will be scanned along one or two chords from centre to edge, then at ten positions around the edge, and ten to fifteen positions near the centre.</p>
<p><b>7. Scratches &amp; Point Defects Method 3 (Digital Images).</b></p>	<p><b>METHOD 3.</b></p> <p>An inspection is then carried out with a dark or bright field microscope, with 5x objective at four positions at each of the following locations:</p> <ul style="list-style-type: none"> <li>a) Within 10mm of the center of the surface.</li> <li>b) Equally spaced along the circumference of a centered, 60 mm diameter circle.</li> <li>c) Equally spaced along the circumference of a centered, 120 mm diameter circle.</li> </ul>



**Advanced LIGO Input Test Mass Coatings**

**8. Durability Test Data & Samples.**

All samples from the durability tests and data, including spectrophotometer scans of the representative coating on each side in an Excel spreadsheet.