



**ALIGO PRE-MODE MATCHING TELESCOPE MIRROR
SUBSTRATE #2, COATED**

AUTHOR:	CHECKED:	DATE	APPROVALS		
			DCN NO.	REV	DATE
R. Martin, D. Reitze		04-01-08			

Applicable Documents

- D080161-00-D ALIGO Pre-Mode Matching Telescope Mirror #2 Substrate
- D080159-00-D ALIGO Pre-Mode Matching Telescope Mirror #2 Blank

Requirements

Physical Configuration

Fabricate from D080161-00-D ALIGO Pre-Mode Matching Telescope Mirror #2 Substrate
Arrow points in the direction of the highly reflective surface.

Surface 1 and 2

- Coating Centered at 1064 nm
- Angle of Incidence 2.88 degrees, P polarization
- Coating Uniformity 1 nm rms – central 40 mm
15 nm p-v over 68 mm
- Absorption < 1 ppm
- Zero surface electrical field

Surface Quality

To comply with Advanced LIGO Component Specification E080136-00-D, SUBSTRATE ALIGO PRE-MODE MATCHING TELESCOPE MIRROR #2 (Page 2): “Scratches and Point Defects”.
Coating to resist abrasion test per MIL-M-13508C

Surface 1: HR coating

- Transmission: <10 ppm at AOI and less than 100 ppm for +/- 2 deg around design AOI
- Scatter: < 22 ppm over central 40 mm diameter aperture

Surface 2: AR coating

- Reflection: < 300 ppm

NOTE:

- Coating manufacturer to provide:
- One (1 in.) witness plate from each coating run
 - Spectrophotometer graphs of Reflectance and Transmittance of HR coating