## LIGO Laboratory / LIGO Scientific Collaboration

LIGO-T0900438-v2

LIGO

16 Jun 2011

## LIGO Vacuum Qualification of First Contact<sup>TM</sup>

Dennis Coyne, Bob Taylor, Liyuan Zhang

Distribution of this document: LIGO Scientific Collaboration

This is an internal working note of the LIGO Laboratory.

California Institute of Technology LIGO Project – MS 18-34 1200 E. California Blvd. Pasadena, CA 91125 Phone (626) 395-2129 Fax (626) 304-9834 E-mail: info@ligo.caltech.edu

LIGO Hanford Observatory P.O. Box 1970 Richland WA 99352 Phone 509-372-8106 Fax 509-372-8137 Massachusetts Institute of Technology LIGO Project – NW22-295 185 Albany St Cambridge, MA 02139 Phone (617) 253-4824 Fax (617) 253-7014 E-mail: info@ligo.mit.edu

LIGO Livingston Observatory P.O. Box 940 Livingston, LA 70754 Phone 225-686-3100 Fax 225-686-7189

http://www.ligo.caltech.edu/

## 1 Regular (clear) First Contact<sup>™</sup>

The allowable flag hydrocarbon outgassing rate, for any First Contact<sup>TM</sup> which is (unintentionally) left in the vacuum system,<sup>1</sup> is ~10<sup>-12</sup> torr-liter/sec. Given the measured flag hydrocarbon outgassing rate of 10<sup>-13</sup> torr-liter/sec/cm<sup>2</sup> (an instrument background limit result) the total accumulated amount of First Contact<sup>TM</sup> which can (unintentionally) remain in the vacuum system is 10 cm<sup>2</sup>. In the H2 interferometer, corner station vacuum volume, there are ~56 optics with HR surfaces in optical cavities<sup>2</sup>. Each of these optics might be cleaned by First Contact<sup>TM</sup>. This implies that the RGA derived limit of residual First Contact<sup>TM</sup> is 0.2 cm<sup>2</sup> per optic.

The limits on contamination induced loss are defined in the COC Requirements Document<sup>3</sup> (and repeated in the UHV Materials List<sup>4</sup>) as < 1 ppm/yr absorption and < 4 ppm/yr scatter loss for any test mass (TM), high reflectance (HR), surface. Since these limits are from all sources, here we allocate  $1/10^{\text{th}}$  of this limit<sup>5</sup> for First Contact<sup>TM</sup>, i.e. < 0.1 ppm/yr absorption and < 0.4 ppm/yr scatter. Using the pump scaling factor (between the optical contamination cavity test and the LIGO vacuum system), the resulting limits on residual First Contact<sup>TM</sup> (unintentionally) remaining in the vacuum system is < 150 cm<sup>2</sup>, based on the scatter loss limit.

Consequently, the most restrictive limit is set by the hydrocarbon outgassing rate to  $0.2 \text{ cm}^2$  per optic. Note that this limit is a result of the mass spectrometer noise floor in the measurement and could be less restrictive if a larger sample is measured.

The amount of residual First Contact<sup>TM</sup> left on an individual optic is expected to be less than 0.2  $\text{cm}^2$  per optic. As a consequence the use of First Contact<sup>TM</sup> is approved for use in aLIGO.

## 2 Red First Contact<sup>™</sup>

See also the RGA results in E1100584 and the optical contamination cavity results in E1000294.

The measured hydrocarbon outgassing rate is 2.4e-14 torr-liter/sec/cm<sup>2</sup>, which corresponds to a total allowable residual amount of red first contact in the vertex vacuum volume of 41.5 cm<sup>2</sup> (see Table below). The residual first contact is most likely to be left along the perimeter. The allowable amounts of residual first contact is given in the following table. The allowable amount of residue,

<sup>&</sup>lt;sup>1</sup> D. Coyne, Vacuum Hydrocarbon Outgassing Requirements, LIGO-T040001. Based on this document, the flag hydrocarbon outgassing rate limit per assembly is  $\sim 10^{-12}$  torr-liter/sec. Rai Weiss has argued that the requirements defined in this document are more restrictive than required since it does not take into account the pumping capacity of the beam tubes and it is likely that initial LIGO requirements suffice. If so, then the requirements are  $\sim 300$  times more lax. In this note, this relaxation of requirements is considered margin in determining the allowable amount of First Contact<sup>TM</sup> which is permitted (unintentionally) to remain in the vacuum system.

<sup>&</sup>lt;sup>2</sup> In the H2 vertex vacuum volume there are 14 optics with HR surfaces in cavities: 2 ITMs, 2 FMs, 1 BS, PR3, PR2, PRM, SR3, SR2, SRM, and 3 MCMs.

<sup>&</sup>lt;sup>3</sup> G. Billingsley et. al., Core Optics Components Design Requirements Document, section 4.2.2.6 of <u>LIGO-T080026-00</u>. The timescale for accumulation (i.e. the time span between in situ re-cleaning of the test mass optics) has been chosen here to be 1 year. It is possible that a somewhat shorter time span could be accommodated.

<sup>&</sup>lt;sup>4</sup> D. Coyne, LIGO Vacuum Compatible Materials List, LIGO-E960050-v3

<sup>&</sup>lt;sup>5</sup> Other potential high hydrocarbon outgassing sources (i.e. sources with polymers) include BOSEM assemblies, AOSEM assemblies, cabling, SEI position sensors, SEI actuators, etc.

Vertex Vacu							
OPTIC	Qty	Dia. (cm)	Circumference (cm)				
ITM	2	34	213.6				
BS	1	37	116.2				
P/SR3	2	26.5	166.5				
P/SR2	2	15	94.2				
P/SRM	2	15	94.2				
MCn	3	15	141.4				
SMn	2	5	31.4				
PMMTn	2	5	31.4				
Fixed Optics	40	5	628.3				
TOTALS	56		1517.4				
ALLOW	ABLE (BA	SED ONL	Y ON HYDROCARBON	OUTGASS	SING)		
	1.00E-12	torr-liter/se	ec/vertex				
	41.5	cm^2 of re	esidual red first contact				
	0.7	er mirror (a	average)				
	0.0	cm^2 of re	er cm of ci	rcumference			
	cm <sup>2</sup> of residual red first contact per optic:						
	ITM		ITM	2.9			
			BS	3.2			
		P/SR3		2.3			
			P/SR2, P/SRM, MCn	1.3			
			SMn, PMMTn, Fixed	0.4			

based on the hydrocarbon outgassing, seems within likely amounts to be inadvertently left on the optic.

The measured rates of loss for optics exposed to the first contact at 1064 nm and high irradiance is:

Absorption: 9.1 x 10<sup>-4</sup> ppm/yr/cm<sup>2</sup>

Scatter: 8.3 x 10<sup>-2</sup> ppm/yr/cm<sup>2</sup>

It is the scatter loss which dominates over absorption loss. The allowable total amount of residual red first contact in the vertex vacuum volume, based on scatter loss, is 275 cm<sup>2</sup>, which is greater than that allowed on the basis of hydrocarbon outgassing. So, just as is the case for regular (clear) first contact, hydrocarbon outgassing measurements dictate the maximum allowed residual material.

Sample Te	est:									
	Material und	er test:	Photonic Cle	aning Techno	logies Red Firs	t Contact				
	units			112.5	cm^2	6 glass slic	ne side			
	absorption	-0.11773	±	0.11012148	ppm/yr	1 sigma				
	scatter	3.283258	±	3.01135829	ppm/yr	1 sigma				
max. normalized absorption			9.11E-04	ppm/yr/unit	2 sigma					
max. normalized scatter			8.27E-02	ppm/yr/unit	2 sigma					
	test turbopump speed (liter/s)			24.391574	torr/liter/sec					
Scaled to	LIGO:									
	LIGO Vacuum Volume			Vertex	LHO Diagonal	End	Comments			
	Quantity (units)			275	670	165	Allowable amount of material area (cm^2)			
							see E0900398 or PSI V049-1-078			
	LIGO ion pumping speed (liter/s)			2800	6800	1700	for pump rates			
							does not include cryo-pump and effective			
	pumping speed ratio (test/LIGO)			0.0087	0.0036	0.0143	pumping from the Beam Tube			
	max. absorption (ppm/yr)			0.002	0.002	0.002	* Limit is < 0.02 ppm/yr for a single source			
	max. scatter	(ppm/yr)		0.198	0.199	0.196	* Limit is < 0.2 ppm/yr for a single source			
* The overall limit on contamination loss on optics for AdL is < 0.5 ppm/yr absorption and < 4 ppm/yr scatter from all sources, per Table 4.										
of the COC Design Requirements Document (T000127-v1). It is assumed that ~20 sources could contribute.										