



# SPECIFICATION

## Mirror Specifications

APPROVALS	DATE	RE V	DCN NO.	BY	CHECK	DCC	DATE
AUTHOR: L. BARSOTTI	3-5-10						
CHECKED:							
APPROVED: D. SIGG							
DCC RELEASE							

### 1 Description

0.5" Ø Flat/Flat mirror @ 532nm

### 2 Material

Corning HPFS 7980 (high purity fused silica, UV grade)  
Grade 0A (Low inclusion class: <0.3 mm<sup>2</sup> cross section, 0.1 mm max. size;  
Homogeneity < 1ppm)

### 3 Dimensions

0.5"Ø +.000/-.005" X .250" ± .020" tk., Plano / Plano

### 4 Wedge

<60 arc seconds

### 5 Surface Roughness

#### Side 1

Super polish  
Surface Roughness: <1Å RMS in CA  
Surface Quality: 10-5

#### Side 2

Commercial Polish  
Surface Roughness: <5Å RMS in CA  
Surface Quality:40-20

### 6 Surface Figure

#### Side 1

Flat < λ/10 at 632.8 over central 80%

#### Side 2

Flat < λ/4 at 632.8 over central 80%

**SPECIFICATION****Mirror Specifications****7 Coating**

Wavelength: 532nm

Angle of incidence: 0°- 45°

**Side 1**

R > 99.95% @ 532nm and AOI 0°- 45°, both s and p pol

**Side 2**

AR coating, R<1% @ 532nm and AOI 0°- 45°, both s and p pol

**Coating vendor to provide:**

1. Two spectrophotometer graphs of the reflectance and transmittance of the HR coatings; one covering the spectrum from 440nm to 1200nm; the other, with increased sensitivity, showing wavelengths from 450nm to 650nm.
2. Spectrophotometer graphs of the reflectance of the AR coating taken as cited above.