



3






 $\sqrt{1.}$  SEAM TO ARRIVE WITH WELD PREPS IN PLACE.

2. TACK ROLL UP WITH CERTIFIED ROD ONLY (PROVIDED BY GNB).

- 3. CARBON STEEL ROLLERS SHALL BE COVERED WITH STAINLESS STEEL PRIOR TO ROLLING TO PREVENT CONTAMINATION.
- 4. SEAM EDGES SHALL BE PREWORKED TO ENSURE ROUNDNESS OF THE FINAL CYLINDER.
- 5. ROLL-UP PLATES MAY HAVE SHEARED EDGES ONLY IF THE SHEARED EDGES ARE THEN RE-CUT WITH A TUNGSTEN CARBIDE TOOL TO REMOVE CONTAMINATION BY THE ROLLING VENDOR. ACCEPTABLE CUTTING METHODS ARE PLASMA, LASER, WATER JET, OR CARBIDE CUTTING.
- 6. FINAL BEVELS TO BE MADE WITH TUNGSTEN CARBIDE TOOLS ONLY.
- 7. PLATES AND ROLL-UPS MUST REMAIN PROTECTED FROM CONTACT WITH CARBON STEEL OR OTHER SOURCES OF CONTAMINATION DURING MOVING, WORKING, AND STORAGE. COVER CARBON STEEL WITH SST OR HEAVY PAPER, AND KEEP PLATES AND ROLL-UPS WRAPPED OR COVERED AT ALL TIMES WHEN NOT BEING PROCESSED.

  8. ALL MATERIAL TO BE MANUFACTURED IN THE UNITED STATES.
- 9. MACHINE THIS AREA TO THE SPECIFIED DIMENSIONS
- 10. THE FOLLOWING ARE NOT ALLOWED: GRINDING, HONING, LAPPING, POLISHING, BUFFING, SANDING, BLASTING.
- 11. NO HYDROCARBONS ALLOWED IN THE COOLANT. COOLANT LIMITS AS FOLLOWS
  - a. WATER LEACHABLE CHLORIDES: 100PPM
  - b. TOTAL HALOGENS (INCLUDING CHLORIDES): 1000PPM
  - c. TOTAL SULFUR: 1000PPM
- 12. A 2"X12" COUPON OF MATERIAL FROM THE SAME LOT OF MATERIAL MUST BE PROVIDED TO GNB
- ETCH HEAT LOT NUMBER AND PART NUMBER WITH A VIBRATORY TOOL WITH A MINIMUM TIP RADIUS OF .005"



DETAIL A SCALE 1:2 WELD PREP DETAIL

