

Michael Zucker wrote:

Refer to: LIGO-E070288-00-V

VRB-

Action on this is required immediately.

David Tanner requests a change in process for REO supermirrors to be used in HAM1,2,3 both sites.

The apparent destruction of coatings on the thin film polarizers last week calls the Liquinox into question. Please refer questions directly to David and copy the group to save time.

Mike

Begin forwarded message:

From: David Tanner <tanner@phys.ufl.edu>
Date: November 8, 2007 14:46:47 EST
To: mike@tristan.mit.edu (Mike Zucker)
Cc: David Reitze <reitze@phys.ufl.edu>, Guido <mueller@phys.ufl.edu>, Volker <quetschke@phys.ufl.edu>, Rodica Martin <rmartin@phys.ufl.edu>, Muzammil A Arain <muzamil@phys.ufl.edu>
Subject: Request for vacuum waiver: 2" REO mirrors

Make the bake 48 hours (2 days). Sorry for the typo.

David

Hi Mike,

This is a request for a waiver on the cleaning procedure for the 2 inch REO mirrors for e-LIGO. We request a variance, in that we use the procedure for E-Beam Coated Optics (HR and AR) in E000007 except that no liquinox be used. We would like to use First Contact instead of steps 4-10. This should be followed by 120 degree C bake for 8 hours.

Thanks,
David

David Tanner 352-392-4718 (voice)
tanner@phys.ufl.edu 352-392-3591 (fax)
2372 New Physics Bldg. / Univ. Florida / Gainesville FL 32611-8440
WWW: <http://www.phys.ufl.edu/~tanner>