



IDENTIFICATION			
C-EJ-CO			
LIGO-E950026-02-B			
REFERENCE NO.		SHT <u>1</u> OF <u>13</u>	
953571 (930212)			
OFFICE		REVISION	
LIGO		6	
MADE BY	CHKD BY	MADE BY	CHKD BY
RJW	WJC	MLT	SWP
DATE	DATE	DATE	DATE
3/7/94	3/10/94	4/9/97	4/10/97

TITLE	LIGO BEAM TUBE EXPANSION JOINTS CONSTRUCTION OPTION
PRODUCT	LASER INTERFEROMETER GRAVITATIONAL-WAVE OBSERVATORY CALIFORNIA INSTITUTE OF TECHNOLOGY

1.0 GENERAL

1.1 Description

This specification defines the technical requirements for the materials, fabrication, and supply of the LIGO Beam Tube Expansion Joints for the construction option. The construction option consists of two Laser Interferometer Gravitational-Wave Observatories. One will be located near Hanford, Washington and the second will be located near Livingston, Louisiana. Each observatory is comprised of 48.75" minimum inside diameter beam tubes with a total length of approximately 25600 feet. Expansion joints will be required over the entire length and will be used to connect the beam tube segments. The expansion joints will have an approximate spacing of 130 feet. The beam tubes and the expansion joints are the key elements of the vacuum system for sensitive interferometer components and optical beams used by the observatories.

1.2 Scope

The scope of work includes calculations, design and detail engineering, fabrication, welding, dimensional control, inspection, nondestructive examination, cleaning and preparation for shipping. Field installation will be by others. The LIGO Expansion Joint design requirements are shown in Section 3.0.

1.2.1 Drawings/Figures

The following drawing(s) and figure(s) form an integral part of this specification:

Figure 1 - Beam tube bellows configuration

Figure 2 - Dimensional limitations

Figure 3 - Fixture for Supporting Expansion Joint During Vacuum Leak Testing

1.2.2 Specifications

Standards of the Expansion Joint Manufacturers Association, Inc. Sixth Edition

ASME Boiler & Pressure Vessel Code, Section II, "Materials", the 1992 Edition with the 1993 Addenda.

ASME Unfired Pressure Vessels, Section VIII, Division 1 as applicable, the 1992 Edition with the 1993 Addenda. Code stamping is not required.

APPROVED	<i>M. Jellison</i>	DATE	<i>April 11, 1997</i>
	<i>J. Jones</i>	DATE	<i>7/25/97</i>
	CBI		
	CALTECH		



IDENTIFICATION			
C-EJ-CO			
TITLE LIGO BEAM TUBE EXPANSION JOINTS CONSTRUCTION OPTION	REFERENCE NO. 953571 (930212)		SHT <u>2</u> OF <u>13</u>
	OFFICE LIGO		REVISION <u>6</u>
PRODUCT LASER INTERFEROMETER GRAVITATIONAL-WAVE OBSERVATORY CALIFORNIA INSTITUTE OF TECHNOLOGY	MADE BY RJW	CHKD BY WJC	MADE BY MLT
	DATE 3/7/94	DATE 3/10/94	DATE <u>4/9/97</u>
			CHKD BY <u>SWP</u>
			DATE <u>4/10/97</u>

ASME Section IX Welding and Brazing Qualification, 1992 Edition with the 1993 Addenda.

ASME Boiler & Pressure Vessel Code Section V, Nondestructive Testing, 1992 Edition with 1993 Addenda. The requirements of this specification (C-EJ-CO) shall have precedence over those in ASME Boiler & Pressure Code Section V, Nondestructive Testing.

CBI Beam Tube Material Specification C-240-EJ.

CBI Coil Material Bake Specification C-CMBS1.

LIGO Specification 1100004, Rev C, "Beam Tube Module Specification", dated May 11, 1993. (Reference only)

LIGO Specification 1100007, Rev 0, "Process Specification for Low Hydrogen, Type 304L Stainless Steel Vacuum Products", dated April 5, 1993. (Reference only)

1.3 Submittals

Information Required with Quotation:

1.3.1 The vendor must state in his quotation that the quotation complies with this technical specification with any exceptions or alternates noted and explained. The purchaser will assume complete conformance unless deviations are noted.

1.3.2 Shop practices, including forming method, lubricants used, cleaning procedures, etc. See paragraph 4.3.3 concerning the use of lubricants.

1.3.3 A sketch or drawing showing the following information:

1.3.3.1 Expansion joint dimensions including thickness and bellows configuration.

1.3.3.2 Expansion joint spring rates for axial, lateral and rotational movements, and the estimated deviation as a percentage of the spring rate.

1.3.3.3 Degree of axial pretension or compression based on a 102 degree F temperature.

1.3.3.4 Design movements



IDENTIFICATION			
C-EJ-CO			
TITLE LIGO BEAM TUBE EXPANSION JOINTS CONSTRUCTION OPTION	REFERENCE NO. 953571 (930212)		SHT. <u>3</u> OF <u>13</u>
	OFFICE LIGO		REVISION <u>6</u>
PRODUCT LASER INTERFEROMETER GRAVITATIONAL-WAVE OBSERVATORY CALIFORNIA INSTITUTE OF TECHNOLOGY	MADE BY RJW	CHKD BY WJC	MADE BY MLT
	CHKD BY SWP	DATE 3/7/94	DATE 3/10/94
	DATE 3/7/94	DATE 3/10/94	DATE <u>4/9/97</u>
			DATE <u>4/10/97</u>

- 1.3.4 Procedures for making and documenting measurements of dimensions with specified tolerances.
- 1.3.5 A description of the vendor's manufacturing facilities and the equipment required to perform the work covered by this specification.
- 1.3.6 A description of the vendor's procurement approach, including source of materials, traceability of materials, and management of subcontracts if applicable.
- 1.3.7 The vendor's quality assurance manual in accordance with ASME Section VIII, Division 1 or ANSI/ASQC Standard Q9001. (Certification is not mandatory).
- 1.3.8 The vendor's management plan, including the process by which the work covered by this specification will be monitored and controlled, and identification and function of key personnel to be assigned.

Information Required For Approval by the Purchaser After Receipt of Order and 4 Weeks Prior to Fabrication:

- 1.3.9 Design calculations and drawings.
- 1.3.10 Weld procedures with supporting procedure qualification records and welder personnel qualification records per ASME Section IX.
- 1.3.11 Shop practices including forming method and lubricants used if required.
- 1.3.12 Helium mass spectrometer leak testing procedures. Leak testing procedures shall comply with ASME Section V, Article 10, Appendix V, which is attached.
- 1.3.13 Certification of qualification for leak testing personnel.

Information Required 2 Weeks Prior to Shipment:

- 1.3.14 Certificates of Compliance for all materials attached to the expansion joint not provided by the purchaser.
- 1.3.15 Helium mass spectrometer leak test report for each expansion joint. The report shall include all requirements of ASME section V Article 10 paragraph T-1091 including the name of the responsible inspector, the specific equipment used including the size of the calibrated leak, helium concentration, the vacuum level during the test, and duration of helium exposure or hold time. The report shall include a statement that



		IDENTIFICATION			
		C-EJ-CO			
TITLE LIGO BEAM TUBE EXPANSION JOINTS CONSTRUCTION OPTION	REFERENCE NO. 953571 (930212)		SHT <u>4</u> OF <u>13</u>		
	OFFICE LIGO		REVISION <u>6</u>		
	MADE BY RJW	CHKD BY WJC	MADE BY MLT	CHKD BY SWP	
	DATE 3/7/94	DATE 3/10/94	DATE 4/9/97	DATE 4/10/97	
PRODUCT LASER INTERFEROMETER GRAVITATIONAL-WAVE OBSERVATORY CALIFORNIA INSTITUTE OF TECHNOLOGY					

the expansion joint has passed the helium leak test to the required sensitivity with the inspector signature.

1.3.16 Record of measured toleranced dimensions and spring rate of each Expansion Joint.

2.0 MATERIALS

- 2.1 The expansion joints shall be manufactured from stainless steel conforming to ASME Specification SA-240 Type 304L (HRAP) and in accordance with CBI Specification C-240-EJ and with LIGO specification 1100007. The thickness of the expansion joints shall be between .100" and 0.103". External attachments shall be ASTM SA240 Type 304L stainless steel.
- 2.2 The purchaser will furnish the vacuum boundary material for the expansion joints. Unless noted otherwise by the manufacturer, the purchaser will furnish only one 60" wide X 156" long sheet of material for each expansion joint. The vendor is responsible to furnish all other materials for the expansion joints.
- 2.4 Weld wire must be cleaned and handled in accordance with CBI Specification WMS-ER308L. The purchaser will provide filler wire if required by vendor.
- 2.5 The material supplied to the vendor will have been subjected to an air bake in accordance with Specification C-CMBS1 prior to receipt by the vendor. The expansion joint manufacturer is not responsible for performing the air bake of the expansion joint material.

3.0 DESIGN

The configuration of the beam tube and expansion joint is illustrated in Figure 1. The following requirements are based on this configuration.

- 3.1 Nominal size: 49.145" inside diameter by 56" maximum outside diameter. The expansion joints will be welded by the purchaser to tubes with a 49.375" outside diameter and a 0.125" thickness. The ends of the tubes will be expanded to 49.375" outside diameter to match the size of the ends of the expansion joints.
- 3.2 Expansion joint type: Single, unreinforced
- 3.3 Flow medium:
 - During installation: dry air, 15 feet per second
 - Operating & Transient: Vacuum < 1 x 10E-9 torr
- 3.4 Design Pressure:



IDENTIFICATION			
C-EJ-CO			
TITLE LIGO BEAM TUBE EXPANSION JOINTS CONSTRUCTION OPTION	REFERENCE NO. 953571 (930212)		SHT <u>5</u> OF <u>13</u>
	OFFICE LIGO		REVISION <u>6</u>
PRODUCT LASER INTERFEROMETER GRAVITATIONAL-WAVE OBSERVATORY CALIFORNIA INSTITUTE OF TECHNOLOGY	MADE BY RJW	CHKD BY WJC	MADE BY MLT
	DATE 3/7/94	DATE 3/10/94	DATE 4/9/97
			CHKD BY SWP
			DATE 4/10/97

External: 14.7 psia Continuous after start up
 Internal: 3.0 psig During construction and operations maintenance

3.5 Temperatures

Transient: _____ 334° F
 Minimum: _____ -16° F
 Maximum operating: _____ 120° F
 Effective installation temperature: _____ 102° F

3.6 Maximum installation movements:

These movements will be one time movements. The movements will be made to assist the fit up of the second joint between the expansion joint and the tube sections.

Axial: ± 0.125" in addition to other specified axial movements
 Lateral: 0.0"
 Rotational: ± 0.13 degrees in addition to other specified rotations

3.7 Maximum movements:

3.7.1 Operating

Axial: 0.262" Contraction, 102° to 120° F
 1.610" Extension, 102° to -16° F
 7483 total cycles (daily cycles for 20.5 years)
 Lateral: 0.04"(5 cycles) The 5 cycles of lateral movement may be caused by differential settlement between supports.
 Rotational: 0.10 degrees (1 cycle) due to dead load of tube
 0.20 additional degrees (5 cycles)

3.7.2 Transient

Axial: 3.46" Contraction (20 cycles) 102° to 334° F.
 Lateral: 0.00"
 Rotational: 0.10 to 0.20 degrees (20 cycles)

3.8 Rods (Tie/Limit/Control): None

3.9 Dimensional limitations: See Figure 2

Nominal Overall length: Per Fabricator ± 0.125"
 Tangents (straight portion of ends): 5" ± 0.125"
 Maximum Outside diameter: 56"



IDENTIFICATION C-EJ-CO

TITLE LIGO BEAM TUBE EXPANSION JOINTS CONSTRUCTION OPTION	REFERENCE NO. 953571 (930212)		SHT <u>6</u> OF <u>13</u>	
	OFFICE LIGO		REVISION <u>6</u>	
PRODUCT LASER INTERFEROMETER GRAVITATIONAL-WAVE OBSERVATORY CALIFORNIA INSTITUTE OF TECHNOLOGY	MADE BY RJW	CHKD BY WJC	MADE BY MLT	CHKD BY SWP
	DATE 3/7/94	DATE 3/10/94	DATE 4/9/97	DATE 4/10/97

Minimum Inside diameter: 48.75"
 Minimum thickness at ends: 0.100"
 Maximum thickness at ends: 0.103"
 Concentricity of straight ends: 0.125"

- 3.10 Spring Rates: (Based on a 70° F material temperature.)
 Axial: 8000 lbs/in Maximum (As measured based on a full stroke per 3.7.2, at 70° F See Paragraph 4.6.7.) Lateral: Supplied by Vendor
 Rotational: Supplied by Vendor
 Torsion: Supplied by Vendor

3.11 Torsional Resistance:

The expansion joint shall be capable of resisting a torsional load of 405,000 inch pounds during operation. There will be a maximum of 30 cycles for this torsional load.

3.12 Installation Position: Horizontal

3.13 Vibration frequency: by Vendor

4.0 FABRICATION

4.1 Material Bake (LIGO Specification 1100007, Section 2.2 & 2.5)

The material will be provided by the purchaser. The expansion joint manufacturer will receive the material in the air baked condition per CBI specification C-CMBS1. The vacuum baking per Section 2.5 of the LIGO Specifications will be performed by others.

4.2 Welding (LIGO Specification 1100007, Section 2.3)

4.2.1 All welding exposed to vacuum shall be done by the gas tungsten arc welding (GTAW) process. Welding shall be autogenous with the exception that weld passes on the outside of the expansion joint may use filler wire meeting the requirements of paragraph 2.3.

4.2.2 All welding of external attachments to the expansion joints shall be made by the GTAW or gas metal arc welding (GMAW) processes. The use of flux cored arc welding (FCAW) is not permitted.



IDENTIFICATION
C-EJ-CO

TITLE LIGO BEAM TUBE EXPANSION JOINTS CONSTRUCTION OPTION	REFERENCE NO. 953571 (930212)		SHT <u>7</u> OF <u>13</u>	
	OFFICE LIGO		REVISION <u>6</u>	
PRODUCT LASER INTERFEROMETER GRAVITATIONAL-WAVE OBSERVATORY CALIFORNIA INSTITUTE OF TECHNOLOGY	MADE BY RJW	CHKD BY WJC	MADE BY MLT	CHKD BY SWP
	DATE 3/7/94	DATE 3/10/94	DATE <u>4/9/97</u>	DATE <u>4/10/97</u>

- 4.2.3 For all welding, use an inert gas purge on the vacuum side of the weld. An inert gas purge shall also be used on the vacuum side when welding seams or attachments on the outside of the expansion joint, including shipping lugs if required.
- 4.2.4 The bellows element shall not be constructed from lap-welded pipe or lap-welded tubing.
- 4.2.5 Unless directed otherwise by the purchaser, temporary attachments and weld tacks for shop fit-up, lifting or handling shall not be used.
- 4.2.6 Welding procedures shall be submitted prior to production welding. Welder and weld operator qualification records shall be submitted prior to any individual performing welding. Welders and weld operator qualifications shall comply with Section IX of the ASME Boiler and Pressure Vessel Code. The purchaser shall have the option to require the requalification of any welder at any time if, in the purchaser's opinion, the welder's qualifications are suspect or welds appear not to be of the proper quality.

4.3 Cleanliness Maintenance and Cleaning

- 4.3.1 All contact made with the stainless steel material during fabrication shall be such as to prevent carbon steel contamination.
- 4.3.2 The expansion joint material shall be protected to maintain cleanliness throughout the entire fabrication procedure. If required, the expansion joint may be cleaned prior to helium mass spectrometer leak testing by wiping with acetone and/or isopropyl alcohol to remove oil, grease and other contaminants. At least 24 hours shall pass between acetone / isopropyl alcohol cleaning and the leak test. After successful testing and just prior to packaging, the expansion joint shall again be cleaned by wiping with acetone and / or isopropyl alcohol if required. A clean white cloth dampened with isopropyl alcohol or acetone shall show no indication of contamination when wiped against the cleaned expansion joint. If lubricants have been used in contact with the expansion joint during fabrication, the expansion joint shall also be steam cleaned with de-ionized water after the solvent wipe. No other cleaning agents shall be used on the expansion joints without the approval of the purchaser. The expansion joint fabricator shall submit a cleaning procedure to the purchaser for approval.
- 4.3.3 Lubricants that affect the ability to obtain high vacuum levels such as silicon lubricants shall not be used during fabrication. It is also preferred that a hydrocarbon based lubricant is not used. If a lubricant must be used, the type of lubricant and the cleaning process shall be provided in a cleaning procedure.



IDENTIFICATION			
C-EJ-CO			

TITLE LIGO BEAM TUBE EXPANSION JOINTS CONSTRUCTION OPTION	REFERENCE NO. 953571 (930212)		SHT <u>8</u> OF <u>13</u>	
	OFFICE LIGO		REVISION <u>6</u>	
PRODUCT LASER INTERFEROMETER GRAVITATIONAL-WAVE OBSERVATORY CALIFORNIA INSTITUTE OF TECHNOLOGY	MADE BY RJW	CHKD BY WJC	MADE BY MLT	CHKD BY <u>SWP</u>
	DATE 3/7/94	DATE 3/10/94	DATE <u>4/9/97</u>	DATE <u>4/10/97</u>

4.4 Preparation for Shipping

- 4.4.1 Wrap the expansion joints securely in plastic and seal at both ends to maintain a clean state until installation by others. Cover the ends of the expansion joints with a cap to protect the edges and prevent punctures of the plastic wrap. Type of desiccant used to minimize condensation shall be specified.
- 4.4.2 Ship the expansion joints in crates to protect the expansion joint and plastic wrap during shipping. The crates can be sized to hold multiple expansion joints to minimize shipping costs. The crates can be reusable. Provide a procedure specifying how paragraph 4.4.1 will be met, and state what type of crate and quantity will be used.
- 4.4.3 The vendor shall supply three (3) aluminum fixtures that attach to the inside of the expansion joints to maintain the nominal length of the expansion joints during vacuum leak testing. The fixtures shall be designed to resist the 32,000 pound longitudinal compressive load created by the vacuum during leak testing. The fixtures shall be designed to be installed quickly and easily. See Figure 3, "Fixture for Supporting Expansion Joint During Vacuum Leak Testing".

4.5 Dimensional Control

The fabricator shall measure and record all dimensions for which tolerances are specified.

4.6 Fabrication Tolerances

- 4.6.1 Records of measured toleranced dimensions shall include the temperature of the expansion joint during the measurements. Temperatures shall be between 60° and 80° Fahrenheit.
- 4.6.2 The outside circumference of the ends of the expansion joints shall be within $\pm 3/64$ ", of the theoretical circumference corresponding to the specified inside diameter.
- 4.6.3 The ends of the Expansion Joints shall be perpendicular to the cylindrical axis within 0.030".
- 4.6.4 The ends of the expansion joint shall be machined flat within 0.005". The flatness of 0.005" shall be measured while the expansion joint is still restrained in the machine. The ends of the expansion joints shall be flat within 0.030" when the expansion joint is in the unrestrained state.
- 4.6.5 The overall length shall be within $\pm 1/8$ ".



IDENTIFICATION			
C-EJ-CO			

TITLE LIGO BEAM TUBE EXPANSION JOINTS CONSTRUCTION OPTION	REFERENCE NO. 953571 (930212)		SHT <u>9</u> OF <u>13</u>	
	OFFICE LIGO		REVISION <u>6</u>	
PRODUCT LASER INTERFEROMETER GRAVITATIONAL-WAVE OBSERVATORY CALIFORNIA INSTITUTE OF TECHNOLOGY	MADE BY RJW	CHKD BY WJC	MADE BY MLT	CHKD BY <u>SWP</u>
	DATE 3/7/94	DATE 3/10/94	DATE 4/9/97	DATE 4/10/97

4.6.6 The ends of the expansion joint shall be concentric within 1/8 ".

4.6.7 The measured axial spring rate of all expansion joints shall be within a range of 1,000 pounds per inch based on a full stroke per paragraph 3.7.2.

4.7 Surface Finish

Grinding and polishing of the inside surface of the expansion joints is not permitted without the purchasers approval. The expansion joint material is SA204 Tyoe 304L (HRAP), Hot Rolled and Annealed with a surface finish rougher than 2.5 microns RMS.

5.0 INSPECTION

5.1 The Expansion Joints shall be tested with a helium mass spectrometer. The Expansion Joints shall be sealed at both ends, bagged with plastic, and the envelope evacuated and injected with helium to provide an environment exceeding 80% helium surrounding the Expansion Joint. The test sensitivity shall be sufficient to measure a helium leakage rate of 1×10^{-10} atm cc/sec. The mass spectrometer shall be calibrated with a calibrated helium leak with a leak rate of less than 1×10^{-9} std cc / second of helium. Each Expansion Joint shall be evacuated to a pressure consistent with the required test sensitivity. Expansion Joints with helium leakage greater than 1×10^{-10} atm cc / second are unacceptable. Calibration of the leak testing system shall be in accordance with ASME Section V Article 10 Appendix V paragraph V-1062.2 where the calibrated leak is mounted on the system as far away from the helium mass spectrometer as possible.

5.2 The purchaser shall have the option of inspecting at the vendor's facility and witnessing tests or procedures required in this specification.

5.3 Each expansion joint shall be tested to determine the compressive axial spring rate based on the axial movement specified in paragraph 3.7.2 except that only one cycle is required. The temperature of the expansion joint shall be between 60° and 80° F during the test. The spring rate determined by the test (load divided by movement) shall be provided on the expansion joint tag in "pounds per inch".

6.0 MATERIAL AND COMPONENT IDENTIFICATION

6.1 Each expansion joint shall be uniquely identified. The identification shall enable the complete history of each expansion joint to be maintained. A record for each expansion joint shall indicate the welder identification for each joint, all weld repairs, stops and starts, and fabrication abnormalities.



IDENTIFICATION C-EJ-CO

TITLE LIGO BEAM TUBE EXPANSION JOINTS CONSTRUCTION OPTION	REFERENCE NO. 953571 (930212)		SHT <u>10</u> OF <u>13</u>	
	OFFICE LIGO		REVISION 6	
PRODUCT LASER INTERFEROMETER GRAVITATIONAL-WAVE OBSERVATORY CALIFORNIA INSTITUTE OF TECHNOLOGY	MADE BY RJW	CHKD BY WJC	MADE BY MLT	CHKD BY <u>SWP</u>
	DATE 3/7/94	DATE 3/10/94	DATE <u>4/9/97</u>	DATE <u>4/10/97</u>

6.2 Material traceability shall be maintained throughout fabrication and shipping. Material marking and traceability requirements specified in ASME, Section VIII, Division 1 shall apply. Markings if used shall be located on the outside surface on the straight portion of the expansion joint and shall be either marking fluid or vibratory tool with a minimum tip radius of 0.005 in.. See ASME Section II SA-480, paragraph 21.1.1. Chlorine and fluorine contaminants from markers must not exceed the residual levels shown in ASME Section V, paragraph T-641 for liquid penetrant materials. The following markers are approved for use:

<u>MARKER</u>	<u>MANUFACTURER</u>	<u>COLOR</u>
Sharpie or Sharpie Tec Ink	Sanford	Black
Action Markers High Purity Ink	Mark-Tex	White/Black/Red
Marks-A-Lot	Avery-Denison	Black/Red
GP-X Markers	Diagraph	White/Black/Yellow
Mighty Mark 7000, 7007	Fiber-Castell	All
American 7000	Eberhard-Faber	Black
Low Chloride Penemark Metal Marker (Paint)	John P. Nissen	White/Black/Yellow
Tempil Marker or Pyromarker (Paint)	Tempil	All colors except blue

7.0 NON-ESCORT PRIVILEGES AND INSPECTION RIGHT

The National Science Foundation (NSF), Caltech, and the purchaser, through their authorized representatives, have the right to inspect and evaluate the work performed or being performed under this specification, including the premises where the work is being performed at all reasonable times. The NSF and Caltech shall have non-escort privileges to all areas of the facilities where the work is being performed under this specification. This shall include access to fabrication, assembly, cleaning, and test areas for the purpose of monitoring activities. The vendor shall furnish all reasonable facilities and assistance for the safe and convenient inspection of the work if requested. The vendor shall give the purchaser a five day notice of the start of any major fabrication or test activity, or restart of activity after periods of inactivity exceeding a week.



IDENTIFICATION			
C-EJ-CO			

TITLE LIGO BEAM TUBE EXPANSION JOINTS CONSTRUCTION OPTION	REFERENCE NO. 953571 (930212)		SHT <u>11</u> OF <u>13</u>	
	OFFICE LIGO		REVISION 6.	
PRODUCT LASER INTERFEROMETER GRAVITATIONAL-WAVE OBSERVATORY CALIFORNIA INSTITUTE OF TECHNOLOGY	MADE BY RJW	CHKD BY WJC	MADE BY MLT	CHKD BY SWP
	DATE 3/7/94	DATE 3/10/94	DATE 4/9/97	DATE 4/10/97

Note: The expansion joint widths shown in the following sketches is estimated and may be selected by the manufacturer.




FIGURE 1 - CONFIGURATION OF BEAM TUBE AND EXPANSION JOINT



IDENTIFICATION			
C-EJ-CO			
TITLE LIGO BEAM TUBE EXPANSION JOINTS CONSTRUCTION OPTION	REFERENCE NO. 953571 (930212)	SHT 12 OF 13	
	OFFICE LIGO	REVISION 6	
PRODUCT LASER INTERFEROMETER GRAVITATIONAL-WAVE OBSERVATORY CALIFORNIA INSTITUTE OF TECHNOLOGY	MADE BY RJW	CHKD BY WJC	MADE BY MLT
	DATE 3/7/94	DATE 3/10/94	DATE 4/9/97
		CHKD BY SWP	DATE 4/10/97




FIGURE 2 - EXPANSION JOINT DIMENSIONAL LIMITATIONS



IDENTIFICATION			
C-EJ-CO			
TITLE	REFERENCE NO. 953571 (930212)		SHT <u>13</u> OF <u>13</u>
	OFFICE LIGO		REVISION <u>6</u>
PRODUCT	MADE BY RJW	CHKD BY WJC	MADE BY MLT
	DATE 3/7/94	DATE 3/10/94	DATE 4/9/97
	LIGO BEAM TUBE EXPANSION JOINTS CONSTRUCTION OPTION		CHKD BY <u>SWP</u>
LASER INTERFEROMETER GRAVITATIONAL-WAVE OBSERVATORY CALIFORNIA INSTITUTE OF TECHNOLOGY		DATE 4/10/97	




FIGURE 3 - FIXTURE FOR SUPPORTING EXPANSION JOINT DURING VACUUM LEAK TESTING