



SPECIFICATION

aLIGO ISC Optics: 2” Dichroic Splitters

APPROVALS	DATE	RE V	DCN NO.	BY	CHECK	DCC	DATE
AUTHOR: L. BARSOTTI	12-16-10						
CHECKED:							
APPROVED: P.FRITSCHEL							
DCC RELEASE							

1 Description

2”Ø Flat/Flat dichroic splitters (maximum reflection for 1064nm and maximum transmission for 532nm).

2 Material

Corning HPFS 7980 (high purity fused silica, UV grade)
Grade 0A (Low inclusion class: <0.3 mm² cross section, 0.1 mm max. size;
Homogeneity < 1ppm)

3 Dimensions

2”Ø +.000/-.005" X .375" ± .020" tk., Plano / Plano

4 Wedge

30 arc minutes ± 5 arc minutes

5 Surface Roughness

Side 1

Super polish
Surface Roughness: <1Å RMS in CA
Surface Quality: 10-5

Side 2

Super Polish
Surface Roughness: <1Å RMS in CA
Surface Quality: 20-10

6 Surface Figure

Side 1

Flat < λ/10 at 632.8 over central 80%

**aLIGO ISC Optics: 2" Dichroic Splitters****Side 2**

Flat $< \lambda/5$ at 632.8 over central 80%

7 Coating

Wavelength: 1064nm and 532nm

Angle of incidence: 45°

Side 1

R > 99.9% @ 1064nm for **p** polarization

T > 97% (best effort) @ 532nm for **s** polarization

Side 2

AR coating, R < 0.1% (best effort) both for **s-pol @ 532nm** and **p-pol @ 1064nm**

Serial numbers and registration marks shall be scribed or etched on the barrel of the optic for in-vacuum use

Coating vendor to provide:

1. One 1" dia. witness sample from each coating run
2. Two spectrophotometer graphs of the reflectance and transmittance of the HR coatings; one covering the spectrum from 530nm to 1200nm; the other, with increased sensitivity, showing wavelengths from 900nm to 1100nm
3. Spectrophotometer graphs of the reflectance of the AR coating taken as cited above.