


# Extra loss $\sim 40$ ppm / mirror microroughness = 4~5 ppm?

- Visibility, recycling gain, large angle scatterometer, etc are consistent with 150 ppm loss per arm
- known loss per arm
  - » surface figure ( $\lambda > 0.6\text{cm}$ ): 20-30 ppm / mirror x 2
  - » ETM transmission : 7 ppm
  - » absorption : 4ppm / mirror x 2
  - » diffractive loss : 2ppm
- 150 - known = 80 ppm / arm or 40 ppm / mirror

- FFT calculation with phasemaps ( $\lambda > 0.6\text{cm}$ )
- extra loss as a free parameter



# Advanced LIGO

---

- total arm loss budget = 70ppm
- known loss :  $\sim 50$  ppm / arm
  - » diffraction : 0.4 ppm
  - » absorption : 0.5 ppm x 2
  - » surface figure : 20ppm x 2
  - » ETM transmission : 7 ppm
- 11 ppm / mirror for microroughness and all other losses
- LIGO I mirror : 40 ppm

# LIGO



$$loss = C \left( \frac{4\pi\sigma_{1D}}{\lambda} \right)^2$$

## Summary

( $C_{1D \rightarrow 2D} = 1.2$ )

$3.8 \text{ cm}^{-1}$



+ 10 ppm  
non smooth scattering [4]



Liyuan's  
integrating  
sphere

# CSIRO RMS = 0.5 x true RMS



- 1d topo data - tilt - curvature using 1024 data points
  - » rms = 0.17nm
- generate data using spectrum  $f^{-2}$ 
  - » rms = 0.12 using raw data
  - » rms = 0.064 using data with tilt and curvature subtracted
- loss  $\sim \text{rms}^2$



# Integrating sphere data Liyuan

0.2mm beam size


1cm x 1cm 0.1mm step




## Point scattering loss ~ 10ppm

### ● 2ITM04

- » total of 10201 data
- » mean(all)=16, std(all)=109
- » bad points 362 with loss > 20ppm
- » mean(bad)=193, std(bad)=556
- » mean(con)=193 \* 362/10201=7 ppm



|        | cut ppm | bad points | mean (all) | mean (bad) | mean (con) |
|--------|---------|------------|------------|------------|------------|
| 2ITM04 | 20      | 362        | 16         | 193        | 7          |
| 4ITM04 | 30      | 613        | 23         | 95         | 5.7        |
| 4ITM07 | 20      | 882        | 18         | 105        | 9.1        |
| 4ITM08 | 30      | 936        | 25         | 91         | 8.3        |
| ETM04A | 15      | 356        | 12         | 53         | 2          |




point scattering : uniform  
~10 ppm

smooth roughness :  
BRDF( $\theta$ ) $\sim\theta^{-2.45}$

$$\text{loss}(>3.8\text{cm}^{-1}) = (1.5^\circ/380\lambda)^{0.45} \times 15\text{ppm} = 100\text{ ppm}$$

# Fine structure in mm region






# LIGO

## loss per size or

Loss calculated using a bin size :  
assume no loss with spatial  
frequency longer than 1/bin size

$\text{loss}(1/\text{bin}2) - \text{loss}(1/\text{bin}1)$   
= loss coming spatial freq between  
 $1/\text{bin}2 - 1/\text{bin}1$



ering loss (Hiro Yamamoto) @ CIT on April