

BRDF Summary
P-Pol, 1064 nm
5/19/2011

Sample	Angle Incidence	BRDF
Polished SS no oxide, Dan Riley	55	1.12E-04
Polished SS 1 pass, Dan Riley	55	1.20E-02
Polished SS 2 pass, Dan Riley	55	1.39E-02
Polished SS 2 pass, Liyuan	55	1.10E-02
Polished SS 3 pass, Dan Riley	55	1.09E-02
Polished SS 4 pass, Dan Riley	55	1.48E-02
Polished SS, no oxide, Rai Weiss	55	1.00E-03
Polished SS, 4 hr oxide, Rai Weiss	55	1.50E-03
Polished SS, 8 hr oxide, Rai Weiss	55	4.50E-03
Porcelain steel, Rai Weiss	55	1.40E-03
Porcelain steel, wet spray, Liyuan	57	2.00E-02
Porcelain steel, electrostatic, Liyuan	57	1.00E-02

3.00E-03
3.80E-03