

#### LASER INTERFEROMETER GRAVITATIONAL WAVE OBSERVATORY

### **SPECIFICATION**

E1500009 -V1

Drawing No Vers.

Sheet 1 of 2

# aLIGO ISC optics: 2" 90:10 beam splitters

APPROVALS	DATE	RE V	DCN NO.	BY	CHECK	DCC	DATE
AUTHOR: L. BARSOTTI	12-08-10						
CHECKED:							
APPROVED: P. FRITSCHEL							
DCC RELEASE							

## 1 Description

 $1"\emptyset$  and  $2"\emptyset$  90:10 beam splitters @ 1064nm

### 2 Material

Corning HPFS 7980 (high purity fused silica, UV grade) Grade 0A (Low inclusion class: <0.3 mm² cross section, 0.1 mm max. size; Homogeneity < 1ppm)

## 3 Dimensions, Surface Roughness and Figure

 $2"\emptyset + .000/-.005" X .375" \pm .020" tk., Plano / Plano$ 

Wedge: 30 arc minutes  $\pm$  5 arc minutes

**Surface Roughness:** 

Side 1

Super polish

Surface Roughness: <1Å RMS in CA

Surface Quality: 10-5

Side 2

Super Polish

Surface Roughness: <1Å RMS in CA

Surface Quality: 20-10

**Surface Figure:** 

Side 1

Flat  $< \lambda/10$  at 632.8 over central 80%

Side 2

Flat  $< \lambda/5$  at 632.8 over central 80%

#### LASER INTERFEROMETER GRAVITATIONAL WAVE OBSERVATORY

### **SPECIFICATION**

E1500009 -V1

Drawing No Vers.

Sheet 2 of 2

# aLIGO ISC optics: 2" 90:10 beam splitters

### 4 Coating

Wavelength: 1064nm Angle of incidence: 45°

Side 1

90:10 (R:T) for **p** polarization

 $R = 90\% \pm 2\%$ 

Side 2

AR coating, R < 0.1% (best effort) for **p**-polarization

Arrow pointing to side 1, serial numbers and registration marks shall be scribed or etched on the barrel of the optic for in-vacuum use.

### Coating vendor to provide:

- 1. Two spectrophotometer graphs of the reflectance and transmittance of the HR coatings; one covering the spectrum from 530nm to 1200nm; the other, with increased sensitivity, showing wavelengths from 900nm to 1100nm, both for s and p polarization.
- 2. Spectrophotometer graphs of the reflectance of the AR coating taken as cited above.